



**WILKO PAINT**  
2727 Ohio Street  
Wichita, KS 67219  
Tel 800-658-3799  
Fax 316-838-4288

## **COATING RECOMMENDATIONS**

*With Attached Product Data*  
**Coating System No. 43**

**For:** \_\_\_\_\_

**Date:** \_\_\_\_\_

**Prepared By:**

**WILKO PAINT, INC.**

### **SURFACE DESCRIPTION**

Indoor or outdoor above ground steel structures, piping, vessels, tanks, towers, process facilities, etc., operating to 200°F.

### **COATING SYSTEM**

Water borne inhibitive red oxide primer and water borne acrylic gloss topcoat.

### **SURFACE PREPARATION**

**Preferred:** Remove oil, grease, dirt and other surface contaminants. Abrasive blast clean to N.A.C.E. #3 Commercial Blast. Use 16-40 mesh U.S. Sieve series abrasive to provide a 1.0-2.0 mil surface profile.

**Optional:** High pressure water wash to remove chalk and other surface contaminants. Spot prime as needed.

For more information refer to "APPLICATION AND INSPECTION" towards the end of this catalog.

### **PRIME COAT**

**Product**  
**No. Coats**  
**Application**  
**Dry Film Thickness**  
**Wet Film Thickness**

907.15 WB Primer Red (or 902-13 Gray)  
One  
Brush, roller or spray  
2.0-3.0 mils  
5.0-7.0 mils

### **INTERMEDIATE COAT**

**Product**  
**No. Coats**  
**Application**  
**Dry Film Thickness**  
**Wet Film Thickness**

949.902 WB Aluminum  
One  
Spray application preferred  
1.5-2.0 mils  
4.0-6.0 mils

### **TOP COAT**

**Product**  
**No. Coats**  
**Application**  
**Dry Film Thickness**  
**Wet Film Thickness**

949.902 WB Aluminum  
One  
Spray application preferred  
1.5-2.0 mils  
4.0-6.0 mils

**REMARKS:** See Technical Data Sheets for mixing instructions.

Questions: contact Don L. Holt, VP/Technical Sales @ (918) 299-0170 FAX (918) 299-0170  
Mobile/cell # (918) 289-4658, E Mail: donlholt@sbcglobal.net

Please visit our website for more information: [www.wilkopaintinc.com](http://www.wilkopaintinc.com)