



**WILKO PAINT**  
2727 Ohio Street  
Wichita, KS 67219  
Tel 800-658-3799  
Fax 316-838-4288

## **COATING RECOMMENDATIONS**

*With Attached Product Data*  
**Coating System No. 47**

**For:** \_\_\_\_\_

**Date:** \_\_\_\_\_

**Prepared By:**

**WILKO PAINT, INC.**

### **SURFACE DESCRIPTION**

Exterior, above ground steel structures, piping, vessels, tanks, slurries, or process facilities operating to 250°F dry, 350°F intermittent. Ideal for surfaces that are subject to condensation where added corrosion, impact and abrasion resistance is required.

### **COATING SYSTEM**

High solids Novolac 100% Solids Sprayable coating for concrete or steel surfaces .Excellent moisture, abrasion, and corrosion resistance.

### **SURFACE PREPARATION**

**Preferred:** Round off sharp edges. Remove dirt, oil, grease and other surface contaminants. Abrasive blast clean to N.A.C.E. #3 Commercial Blast Clean. Use 16-40 mesh U.S. Series abrasive to produce 1.0-2.0 mil profile.

### **PRIME COAT (Optional)**

**Product**  
**No. Coats**  
**Application**  
**Dry Film Thickness**  
**Wet Film Thickness**

Wilko 859-06 Ethyl Silicate Inorganic Zinc  
One  
Brush, or spray. (Spray Preferred)  
3 mils  
5 mils

### **Finish Coat COAT**

**Product**  
**No. Coats**  
**Application**  
**Dry Film Thickness**  
**Wet Film Thickness**

Wilko Novolac 332.100 or 332.140  
One or Two  
Brush or Spray (Spray Preferred)  
10 mils each coat  
10 mils each coat

### **2nd TOP COAT (Optional)**

**Product**  
**No. Coats**  
**Application**  
**Dry Film Thickness**  
**Wet Film Thickness**

If color & Gloss retention is required  
721.52 Wilkothane HS White  
One  
Brush or Spray (Spray Preferred)  
3 Mils  
5 Mils

**REMARKS:** See Technical Data Sheets for mixing instructions.

Questions: contact Don L. Holt, VP/Technical Sales @ (918) 299-0170 FAX (918) 299-0170  
Mobile/cell # (918) 289-4658, E Mail: donlholt@sbcglobal.net

Please visit our website for more information: [www.wilkopaintinc.com](http://www.wilkopaintinc.com)