

COATING RECOMMENDATIONS

With Attached Product Data Coating System No. 26

For:	Date:
Prepared By:	WILKO PAINT, INC.
SURFACE DESCRIPTION	Exterior, above ground steel structures, piping, vessels, tanks, towers, or process acilities operating to 250°F continuous, 300°F intermittent.
COATING SYSTEM	High solids epoxy mastic prime coat with twocomponent acrylic polyurethane topcoat for application to minimally prepared steel surfaces. Also as a repair system for damaged urethane coatings. May be applied to previously painted surfaces. Excellent weatherability, color and gloss retention, and corrosion resistance.
SURFACE PREPARATION	Preferred: Round off sharp edges. Remove dirt, oil, grease and other surface contaminants. Abrasive blast clean to N.A.C.E. #3 Commercial Blast Clean. Use 16-40 mesh U.S. Series abrasive to produce 1.0-2.0 mil profile. Optional: Remove surface contaminants by high pressure wash. Hand or power tool clean to remove loose rust and scale.
PRIME COAT	
Product	339.03 Wilkopon Aluminum Mastic or
No. Coats	332.54 Wilkopon Pearl Gray Mastic One
Application	Brush, roller or spray
Dry Film Thickness	8.0-10.0 mils
Wet Film Thickness	10.0-12.5 mils
INTERMEDIATE COAT Product	None
No. Coats	None
Application	
Dry Film Thickness	
Wet Film Thickness	
TOP COAT	
Product	721.52 Wilkothane HS White (colors)
No. Coats	One or Two
Application	Brush, roller or spray
Dry Film Thickness	2.5-3.0 mils per High Solids coat
Wet Film Thickness	4.0-5.0 mils per High Solids coat
REMARKS: 1. See Technical Data Sheets for mixing instructions.	
2. If mold/mildew is a problem, use 721.104 Wilkothane HS MR in place of 721.52	
3. Add 1-2 ounces of T022 per gallon of mixed material of 721.52 Wilkothane HS to compensate	
for cold temperatures. Caution: the ac of mixed material especially in hot wea	
4. Use 342.46C or 347.67C Activator if the ambient or surface temperature is below 70°F.	

Please visit our website for more information: www.wilkopaintinc.com